

Patent Abstracts of Japan

PUBLICATION NUMBER : 06073264  
PUBLICATION DATE : 15-03-94


APPLICATION DATE : 22-06-93  
APPLICATION NUMBER : 05150284

APPLICANT : POLYPLASTICS CO;

INVENTOR : ICHIKAWA TETSUYA;

INT.CL. : C08L 51/06 C08K 5/17 C08K 5/3445  
C08K 5/49 C08K 7/00 C08L 67/00

TITLE : POLYESTER RESIN COMPOSITION  
AND ITS PRODUCTION



ABSTRACT : PURPOSE: To obtain a polyester resin comps. which is excellent in moldability and gives a molded article high in toughness and impact resistance, light in wt., and good in appearance by adding a specific epoxidation promoter to a mixture of a polyester resin with a specific modified polyolefinic resin in melt mixing the two resins.

CONSTITUTION: This resin compsn. is prepd. by compounding 100 pts.wt. resin component comprising 97-30 pts.wt. thermoplastic polyester resin and 3-70 pts.wt. modified polyolefinic resin obtd. by heating a mixture comprising 100 pts.wt. polyolefinic resin, 0.1-15 pts.wt. glycidyl compd. of the formula (wherein R is H or alkyl; and Ar is a glycidylated arom. hydrocarbon group), and 0.01-1.5 pts.wt. free-radical initiator with 0.1-2 pts.wt. epoxidation promoter selected from the group consisting of a t-amine, its salt, a phosphonium salt, and an organometallic complex and 0-120 pts.wt. fibrous, particulate, platy, or hollow filler.

COPYRIGHT: (C)1994,JPO&Japio